



2025

## **DECLARATION OF PERFORMANCE (DOP)**

## Category 1 Aggregate Concrete Masonry Units No. MU003

#### 1. Unique identification of Product type:

Description	Mean Strength N/mm <sup>2</sup>	Dimensions (Length – Width- Height) mm		
		Length	Width	Height
4" Block	13N/mm2 (Capped)	440	100	215
	н			

# 2. Type batch or serial number or any other element allowing identification of the construction product as required under Article 11 (4) of the CPR:

The production details are traceable by the delivery note.

#### 3. Intended use/s:

IS EN 771-3 2011 & BS EN 771-3 2011 – Aggregate Concrete Masonry Units intended for use in load bearing or non-load bearing buildings and civil engineering end uses

#### 4. Manufacturer:

Robinson Concrete, 86 Cumber Road, Claudy , Co Londonderry BT47 4JA.

#### 5. Authorized representative:

Mr. Scott Robinson

#### 6. System of AVCP:

System 2+

#### 7. Harmonized standard:

EN 771-3 Specification for Masonry units Part 3: Aggregate Concrete Masonry Units (Dense & Lightweight aggregates)

#### 8. Notification certification body:

NSAI

### 9. Declared performance:

Essential characteristics	Declared Performance	Technical Reference
Dimensional Tolerance	D1	SR325
Configuration	Group 1	SR325
Gross Density (Direct Airborne Sound Insulation)	2050 kg/m <sup>3</sup>	EN 772-13
Compressive Strength (Mean)	13 N/mm <sup>2</sup> (Capped)	EN 772-1 & SR325
Unit Category	Category 1	Table 14 SR325
Direction of Load	Perpendicular to bed faces	
Dimensional Stability – Moisture Movement	<0.6mm/m	EN 772-14
Reaction To Fire	Class A1	Technical Guidance Document B-Fire Safety
Durability Against Freeze Thaw	Suitable for use in: Masonry Condition Situations A1,A2 & A3 as outlined in Table 14 of S.R. 325:2013 + A2:2018. (Work below or near external ground level) - MX2. 1/2.2 -Mean compressive strength≥13N N/mm <sup>2</sup> -Aggregate in accordance with I.S. EN 12620 and S.R 16 -Mortar Strength Class M4 for A1, M6 for A2 & M12 for A3	SR325
Shear Bond Strength	0,15N/mm <sup>2</sup>	(Tabulated Value)
Flexural Bond Strength	0,5N/ mm <sup>2</sup>	(Tabulated Value)
Water Absorption	<10g/m <sup>2</sup> s	EN 772-11
Water Vapour Permeability	5/15u	EN 1745 Annex A (Tabulated Value)
Thermal Resistance *Dangerous Substances	1.11 W/mK(110, dry, ) NPD	(Tabulated Value)
Deleterious material	Negligible	SR 16:2016

Signed for and on behalf of Robinson Concrete by:

Scott Robinson

Director

Place & date of issue:

86 Cumber Rd, Claudy 11-02-2025